

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client : Big Panda 5 Judds C Slacks Cre	•		Test Number Issue Date Print Date	r : : :	20-00552 18/11/202 18/11/202	20			
Sample Description	Clients Ref : "8mm Laminate" Rigid engineered flooring Colour : Timber/Grey Nominal Composition : HDF Nominal Mass per Unit Area/Density : Nominal Thickness : 8mm	8.8kg/m2							
ISO 9239.1-2003	Reaction to Fire Tests for Floorings. Radiant Heat Source	Determination	of the Burning Be	ehavi	our using a				
	Date of Sample Arrival								
	Date Tested	17/11/2020							
	CHF Value	1	2	3	Mean				
	Length	6.1	6.5 6	.3	6.3	kW/m²			
	Width	≥11	-	-	-	kW/m²			
	HF-30 Value	1	2	3	Mean				
	HF-30 Value Length	1 6.1	2 6.7 6		Mean 6.4	kW/m²			
						kW/m² kW/m²			
	Length		6.7 6 -		6.4				
	Length Width	6.1 -	6.7 6 - 2	.3	6.4				

220871 Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

47526

Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

IATA

the Managing Director of AWTA Ltd.

Page 1 of 2





12

(C)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	Big Panda Flooring	Test Number	:	20-005529
	5 Judds Court	Issue Date	:	18/11/2020
	Slacks Creek QLD 4127	Print Date	:	18/11/2020

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

220871

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

47526

Accredited for compliance with ISO/IEC 17025 - Testing

Page 2 of 2





Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA

Samples and then internativing descriptions have been provided by the client diffess of there was stated. AW FA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

12

APPROVED SIGNATORY

C