

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400


TEST REPORT

Client :	Big Panda F 5 Judds Cou Slacks Cree	0		Test Number Issue Date Print Date	: : :	20-005528 5/11/2020 5/11/2020
Sample [Description	Clients Ref : "Laminate" Rigid flooring planks Colour : Timber Nominal Composition : HDF Nominal Mass per Unit Area/Density : Nominal Thickness : 8mm	8.8kg/m2			
4586-2013 pendix A		Slip Resistance Classification of new P Wet Pendulum Test Method	Pedestrian Surfa	ace Materials		

Date of Testing		05/11/2020					
Test Temperature (20±5degC)	22	°C					
Sample Preparation	Washed with pH neutral detergent and dried.						
Test Direction	Length						
Fixed/Unfixed					Unfixed		
Slider No 96 Batch No					95		
Length	1	2	3	4	5	SRV	
British Pendulum Number Classification	26	27	26	26	26 P2	26	
Oldoomodion					ΓZ		

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 08/11/2019 Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.



APPROVED SIGNATORY

MANAGING DIRECTOR